

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
4 March 2004 (04.03.2004)

PCT

(10) International Publication Number
WO 2004/018197 A1

(51) International Patent Classification⁷: **B32B 17/10**,
27/06, 31/00

(74) Agent: DOBSON, Kevin, S.; E.I. Dupont De Nemours
And Company, Legal Patent Records Center, 4417 Lan-
caster Pike, Wilmington, DE 19805 (US).

(21) International Application Number:
PCT/US2003/026193

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC,
SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA,
UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(22) International Filing Date: 20 August 2003 (20.08.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/404,700 20 August 2002 (20.08.2002) US

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,
SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant (*for all designated States except US*): **E. I. DU
PONT DE NEMOURS AND COMPANY** [US/US]; 1007
Market Street, Wilmington, DE 19898 (US).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **ELWAKIL, Hamdy**
[US/US]; 10 Rivendell Court, Hockessin, DE 19707
(US). **ROMAN, Ronald** [US/US]; 13 Woodridge Drive,
Hockessin, DE 19707 (US). **SMITH, Rebecca, L.**
[US/US]; 8 Merrywood Lane, Vienna, WV 26105 (US).
TANG, Chaucer, C. [US/US]; 407 Manor Drive, Kennett
Square, PA 19348 (US).

Published:

- with international search report
- before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments

*For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.*

(54) Title: DECORATIVE LAMINATED SAFETY GLASS

(57) Abstract: The present invention is a decorative laminated article comprising an image bearing thermoplastic interlayer wherein the image has been printed on the interlayer using an ink jet printing process, wherein the pigment comprises at least one pigment selected from the group consisting of: PY 120; PY 155; PY 128; PY 180; PY 95; PY 93; PV19/PR 202; PR 122; PB 15:4; PB 15:3; and PBI 7. The interlayer material of the present invention can be, for example, PVB, PET, or polyurethane.



WO 2004/018197 A1

THIS PAGE BLANK (USPTO)

DT09 Rec'd PCT/PTO 11 JAN 2005

TITLE**DECORATIVE LAMINATED SAFETY GLASS****CROSS REFERENCE SECTION**

This application claims priority under 35 USC §119 to U.S.

- 5 Provisional Application No. 60/404,700, filed August 20, 2002, and to U.S. Provisional Application Serial No 60/483,515, filed June 26, 2003.

BACKGROUND OF THE INVENTION

- The present invention relates to decorative laminates bearing images printed on an interlayer by a process of ink jet printing. The present invention particularly relates to decorative laminates wherein the image has been printed onto an interlayer comprising polyvinyl butyral (PVB). The present invention also relates to ink formulations that are useful for preparing the laminates of the present invention.
- 10

- Decorative laminates are known and obtained by various processes. DE 29706880, U.S. Pat. No. 4,968,553, U.S. Pat. No. 5,914,178, EP 1129844A1, and DE 20100717 disclose making decorative glass laminates via a silk screening process. Silk-screening an image onto an interlayer is a very time-consuming and expensive process for making decorative laminated safety glass. A process for making decorative glass laminates has also been described in U.S. Pat. No. 4,173,672. This patent describes a transfer lamination process wherein an image printed on paper is transferred to a thermoplastic film, and the film bearing the transferred image is then laminated between glass sheets.
- 15
- 20

- Use of "ink jet" technology to print on PVB and polyurethanes using dye based inks for laminated safety glass has been disclosed in WO0218154. Ink jet printing is known and is a conventional process for printing wherein ink droplets are propelled through a printing head at a high speed towards a printing substrate. Ink jet technology is very flexible because any digital image can be printed onto a substrate.
- 25

- However, a disadvantage of printing directly on PVB using an ink jet printing process is that PVB interlayers have a roughened surface pattern (Rz from 30-60 μm) that can cause poor image quality in a printed image.
- 30

The roughened surface pattern is necessary in a PVB lamination process to obtain laminates free of air bubbles and other defects caused by the presence of trapped air during the lamination process. However, when ink jet printing onto PVB, the rough surface pattern can effect image quality with respect to mottle and resolution.

Other problems with conventional processes for ink-jet printing are encountered due to the inks used in conventional ink-jet processes. Low viscosity inks are required in a conventional ink jet printing process to alleviate high pressure build-up in the print head of the ink jet printer, and subsequent damage to the head and/or poor quality in the printed image. Ink jet printing is carried out conventionally by either (a) drop on demand (DOD) processes, such as a piezo electric printing or thermal ink jet printing processes, or (b) continuous drop ink jet printing. There are other factors as well that make low viscosity inks necessary and preferable in ink jet printing processes. However, use of conventional inks that are suitable for ink jet printing can result in poor image quality on a thermoplastic interlayer. Poor image quality can be the result when a low viscosity ink is sprayed onto a roughened surface such as a PVB surface that has been prepared for lamination, due to ink running from high points to low spots on the interlayer surface.

Another potential problem with printing an image on an interlayer prior to lamination onto another substrate is that the adhesive bond between the interlayer and the substrate can be significantly weakened due to colorant on the surface of the interlayer that can reduce the "effective" bonding surface area between the substrate and the interlayer. By "effective bonding surface" it is meant to describe that surface area where the interlayer and the substrate are in direct contact with each other without an intervening colorant layer. Reduction of the adhesive force of the laminate can result in the laminate having poor performance as a safety glass, or in the application for which it was intended.

The Applicant has developed a system for ink jet printing on thermoplastic interlayers in such a way that when laminated to a substrate,

the laminate maintains its strength and resilience against breakage, while at the same time a quality image is produced on the interlayer printing substrate.

SUMMARY OF THE INVENTION

5 In one aspect, the present invention is a process for obtaining a decorative laminate having a laminate adhesive strength of at least about 1000 psi, the process comprising the steps: ink-jet printing a digital image onto at least one surface of a thermoplastic interlayer; and laminating the image-bearing interlayer between two transparent sheets of a suitable
10 lamination substrate.

 In another aspect, the present invention is a process for ink jet printing a digital image onto a thermoplastic interlayer, the process comprising the step of jetting either an aqueous or solvent-based pigmented ink onto a roughened interlayer surface, the surface having an
15 R_z of from about 30 μm to about 60 μm and a Frequency of greater than about 0.9 cycles/mm, wherein the ink has a viscosity that is sufficiently low that it can be jetted through an ink jet printing head without heating the printing head above ambient temperature.

 In another aspect, the present invention is a decorative laminate
20 comprising at least one sheet of interlayer material bearing an image on at least one surface of the interlayer sheet, wherein the image was printed using an ink jet printing process comprising the step of jetting either an aqueous or solvent-based pigmented ink onto a roughened interlayer surface, the surface having an R_z of from about 30 μm to about 60 μm and
25 a Frequency of greater than 0.9 cycles/mm, wherein the ink has a viscosity that is sufficiently low that it can be jetted through an ink jet printing head without heating the printing head above ambient temperature.

 In another aspect, the present invention is a thermoplastic interlayer
30 sheet bearing an image on at least one surface of the interlayer sheet, the image being printed on the sheet by a process comprising the step jetting either an aqueous or solvent-based pigmented ink onto a roughened

interlayer surface, the surface having an R_z of from about 30 μm to about 60 μm and a Frequency of greater than 0.9 cycles/mm, wherein the ink has a viscosity that is sufficiently low that it can be jetted through an ink jet printing head without heating the printing head above ambient temperature.

DETAILED DESCRIPTION OF THE INVENTION

In one embodiment, the present invention is a method for printing an image onto a thermoplastic interlayer material by an ink jet printing process. A suitable thermoplastic interlayer material for the purposes of the present invention can be any conventionally known or commercially available thermoplastic material which is flexible enough yet rigid enough to be passed through an ink jet printer. An interlayer of the present invention can have any thickness which can be accommodated on an ink jet printer, but typical interlayers thicknesses are in a range of from about 30 mils to about 60 mils. Suitable thermoplastic materials include polyurethane (PUR), polyesters such as polyethylene terephthalate (PET), ethylene/vinyl acetate copolymers (EVA), polyvinyl chloride (PVC), and polyvinyl butyral (PVB), polyolefins such as polyethylene and/or polypropylene, for example. Preferred for the purposes of the present invention is PVB. PVB is available commercially from E.I. DuPont de Nemours & Co., under the tradename of Butacite®, for example.

Ink jet printing onto an interlayer material of the present invention is preferably conducted using a pigmented ink. Pigmented inks can provide image quality that is superior to using dyes in the present application. Pigmented inks are preferred because of their color-fastness, thermal stability, edge definition, and low diffusivity on the printed substrate. In conventional practice, the pigment is suspended in a liquid medium that is conventionally referred to as the "vehicle". Pigments suitable for use in the practice of the present invention can be dispersed in either an aqueous or a non-aqueous vehicle. A "non-aqueous" vehicle suitable for use herein can include water in some minor proportion (no greater than 16 wt%) when particular organic solvents are used. It can be preferable in

some cases to include an organic solvent or solvents in an aqueous-based vehicle to improve jettability of an ink. Various conventional solvents are known and can be used. Useful, but less preferred, solvents include, for example, methyl isobutyl ketone (MIBK), methyl ethyl ketone (MEK),
5 butyrolactone, and cyclohexanone. Suitable solvents include propylene glycol ethers, propylene glycol ether acetates, and ethylene glycol butyl ethers. In a preferred embodiment, dipropylene glycol monomethyl ether acetate (DPMA) is the primary solvent used to disperse the pigmented ink. Mixtures of DPMA with glycol ethers are also preferred.

10 Whether non-aqueous based, aqueous based, or a mixture of aqueous and non-aqueous based vehicles, inks of the present invention have a viscosity that is sufficiently low that they can be jetted through a printing head of an ink jet printer without the necessity of heating the print head in order to lower the viscosity of the ink. In the practice of the
15 present invention, the ink viscosity is below about 30 centipoise (cps), as measured at 25 °C. Preferably the ink viscosity is below about 20 cps at 25 °C. More preferably the ink viscosity is below about 15 cps, and most preferably below about 12 cps at 25 °C.

Without being held to theory, the Applicants believe that problems
20 with image quality using ink jet printing systems can result because ink systems used for jet printing have a much lower viscosity than, for example, inks used in a silk screen printing process. The low viscosity ink can "run" by gravity into the valleys of a roughened PVB surface. The inks, therefore, can form puddles in the low areas on the surface of the
25 PVB, and will not adhere uniformly to the high spots. Therefore, while a low viscosity ink is preferred, the viscosity should not be so low that the image quality is poor in the laminate, or that misting occurs during the printing process. Preferably the ink has a viscosity above about 1 cps. For DOD printing processes, the ink preferably has a viscosity above
30 about 1.5 cps, more preferably above about 1.7, and most preferably above about 1.8 cps measured at 25°C. Viscosity of the inks are determined according to DuPont Standard Test Methods.

Preferable inks for use in the practice of the present invention are those that provide printed images having a satisfactory combination of image quality, and light fastness. Further, laminates that incorporate image-bearing interlayers of the present invention should have the

5 adhesion properties described herein. Due to the nature of the polymeric interlayer substrates used herein for printing, and the requirements for adhesion in a safety glass, choice of a suitable ink is not problem free. An ink suitable for use in the practice of the present invention must also be compatible with the substrate to give satisfactory results. It has been

10 discovered that suitable inks for use in the practice of the present invention can be obtained using the pigments selected from the group consisting of: PY 120; PY 155; PY 128; PY 180; PY 95; PY 93; PV19/PR 202; PR 122; PB 15:4; PB 15:3; and PBI 7. One skilled in the art would know that the designations above are color index numbers for the various

15 pigments. Suitable pigments and ink sets for use in the practice of the present invention are also described in U.S. Provisional Patent Application Serial No. 60/483516, filed June 26, 2003, entitled "Non-Aqueous Inkjet Ink Set", incorporated by reference herein as if fully set forth.

Weatherability, that is the ability of a pigment or dye to hold its

20 original color after prolonged exposure to the environment, is a key concern for an ink set useful in the practice of the present invention. Weatherability can be assessed by accelerated weathering of color blocks, according to ASTM G90 cycle 2. Weathered samples can be weathered in a range of from 120 KLangley (approximately 1 year of natural

25 exposure) to 1,200 KLangley (approximately 10 years of natural exposure). Suitable pigments for use herein typically have a Delta E (that is, the magnitude of change in the E value) after accelerated weathering of less than or equal to about 8, preferably the Delta E is less than about 3.5, more preferably less than about 2.5, and most preferably less than about

30 2.0 on samples that have 480 KLangley exposure times. Delta E is determined from L, a*, and b* color measurements according to the following equation:

Delta E = $[(L_i - L_w)^2 + (a_i^* - a_w^*)^2 + (b_i^* - b_w^*)^2]^{1/2}$, where L_i , a_i^* , and b_i^* are initial color measurements and L_w , a_w^* , and b_w^* are color measurements after weathering. L , a^* , and b^* are color scale axes that are conventionally used to describe the degree of lightness, i.e.

5 black/white (L), red/green (a^*), and blue/yellow (b^*) in an image. A Delta E of less than about 10 is suitable in the practice of the present invention. One of ordinary skill in the printing art would know how to interpret the Delta E values presented herein, but for sake of comparison, a Delta E of from about 2 to 5 would be acceptable to an untrained eye without a
10 control for comparison, and a Delta E of less than about 1.5 would not be detectable to the human eye. It has been found in particular that yellow pigments conventionally known for light-fastness and weatherability did not perform as expected in the practice of the present invention, while other pigments gave surprisingly good performance in the practice of the
15 present invention. These unexpected results can, without being held to theory, be ascribed to a synergistic relationship between these unexpectedly superior pigments and the polymeric substrate.

Printing heads useful for piezo electric processes are available from, for example, Epson, Seiko-Epson, Spectra, XAAR and XAAR-
20 Hitachi. Printing heads useful for thermal ink jet printing are available from, for example, Hewlett-Packard and Canon. Printing heads suitable for continuous drop printing are available from Iris and Video Jet, for example.

Optionally included in an ink system of the present invention is a
25 binder resin. A binder resin can be preferable to improve adhesion between the ink and the laminate substrate. Suitable binders for use in the practice of the present invention include polyvinyl pyrrolidone/vinyl acetate (PVP/VA), polyvinyl pyrrolidone (PVP), and PUR, for example. Mixtures of binder resins can also be useful in the practice of the present
30 invention. Other binders are conventionally known and can be useful herein.

In one embodiment, the inks of the present invention do not include a binder. Typically binders are desirable in order to increase the affinity of an ink to the substrate. However, added binder can increase the viscosity of an ink such that the viscosity is too high for printing according to the process of the present invention. The Applicants have surprisingly discovered that a desirable level of adhesion in a laminate of the present invention can be obtained by use of a preferred solvent together with a pigment, allowing the Applicants to reduce or eliminate the binder in the ink.

Traditionally, pigments are stabilized to dispersion in a vehicle by dispersing agents, such as polymeric dispersants or surfactants. More recently, so-called "self-dispersible" or "self-dispersing" pigments (hereafter "SDPs") have been developed that are suitable for use in the practice of the present invention. SDPs are dispersible in an aqueous vehicle without the use of traditional dispersants. The pigment particles of this invention may be stabilized according to several methods. The pigment particles can be made self-dispersing by a surface treatment as described in, for example, WO01/94476, herein incorporated by reference for all purposes as if fully set forth, or the pigment particles can be stabilized by treatment with dispersant in the traditional way, or the pigments can be dispersed by some combination of surface treatment and traditional treatment.

Preferably, when a traditional dispersant is employed, the dispersant can be a random or structured polymeric dispersant. Preferred random polymers include acrylic polymer and styrene-acrylic polymers. Most preferred, however, are structured dispersants which include AB, BAB and ABC block copolymers, branched polymers and graft polymers. Some useful structured polymers are disclosed in U.S. Pat. No. 5,085,698, EP-A-0556649 and U.S. Pat. No. 5,231,131, which are incorporated herein by reference for all purposes as if fully set forth.

An important parameter in the practice of the present invention is the Frequency of the roughened interlayer surface onto which is to be

printed an image. The Frequency of the roughened surface can be calculated using data obtained from profilometer data. In the practice of the present invention, a suitable Frequency is above about 0.90 cycles/mm. It is preferable that the Frequency be in the range of from about 0.90 cycles/mm to about 3 cycles/mm. More preferably, the Frequency is in the range of from about 1.0 to about 2.9, and most preferably the Frequency is in the range of from about 1.1 to about 2.5 cycles/mm. Above the upper limit significant improvement in the image quality may not be observed. Below the lower limit, the image quality may be poor.

In another embodiment, the invention is a laminate comprising an image-bearing thermoplastic interlayer of the present invention. The interlayer can be laminated together with various transparent substrates such as, for example, glass or polycarbonate. Preferably, the image-bearing interlayer sheet is laminated between at least two sheets of glass. Other layers of interlayer can be positioned between the image-bearing interlayer and the glass, for example as in a glass/"conventional PVB"/"printed PVB"/glass laminate, wherein the printed PVB surface is in contact with the conventional PVB interlayer surface. Conventional laminating techniques are useful and effective in obtaining laminates of the present invention.

As a rule of thumb, the Applicants have found that the adhesion of an image-bearing laminate of the present invention can depend on the level of adhesion of the individual inks used to form the image, as well as the relative amount of each ink used in forming the image. For example, it can be expected that the adhesion of an image-bearing laminate of the present invention will be no lower than the lowest adhesion demonstrated by an individual ink in a given color set, and no higher than the highest adhesion demonstrated by an individual ink in that same ink set. Thus, a laminate of the present invention has adhesion which is a composite of the adhesion of the various inks used in the color set, and likely to be

intermediate between the lowest and highest adhesion levels of the individual inks, depending on formulation.

The composite adhesion of a particular ink formulation suitable for use herein should be at least about 1000 psi, as measured by a compressive shear test. If individual inks of a formulation do not exhibit adhesion of at least 1000 psi, a suitable laminate can still be obtained if they are not included in the formulation in an amount substantial enough to lower the composite adhesion to less than about 1000 psi. By way of illustration, consider an ink formulation "K" which includes individual inks A, B, C, and D -- each having adhesion of 1500 psi, 1300 psi, 1200 psi, and 850 psi, respectively. An image-bearing laminate suitable for the practice of the present invention could still be obtained from K by preparing the formulation such that D is not included in an amount significant enough to lower the adhesion of the laminate. However, it is preferred that each ink in the ink formulation exhibit adhesion of at least about 1000 psi.

In any event, a laminate of the present invention has overall adhesive strength of at least about 1000 psi, which is a level of adhesion suitable for safety glass applications. Preferably the adhesion is at least about 1400 psi. More preferably, the adhesion of a laminate of the present invention is greater than or equal to about 1500 psi, and even more preferably greater than or equal to about 1700 psi. Most preferably the laminate has an adhesive strength of greater than or equal to about 1800 psi.

Laminates of the present invention can be used in any application wherein conventional (that is, non-decorative) laminated glass is used. In addition to the conventional uses as safety glass, however, the laminates of the present invention can be used as decorative articles such as picture windows, decorative countertops, graphic art, image-bearing store-front windows, displays bearing company logos, advertising media, and/or any other use wherein a transparent laminate bearing an image can be desirable.

Laminates of the present invention can be obtained from the image-bearing interlayer and known materials useful for producing safety glass or windows, such as glass or polycarbonate, for example. Lamination of the interlayer to the other components can be accomplished using

5 conventional lamination techniques. For example, an image-bearing interlayer can be laminated to glass by pressing the interlayer between two sheets of glass at an elevated temperature and pressure, under conditions by which air bubbles can be removed or prevented from being trapped in the laminate article.

10 In another embodiment, the present invention is an image-bearing interlayer sheet that has been printed on according to the process described herein. A printed interlayer sheet of the present invention can be laminated with other suitable interlayer materials, such as PET, PUR and/or PVB, to obtain a stacked interlayer that can in turn be laminated
15 with a suitable substrate of the present invention, such as glass or polycarbonate for example.

An image-bearing interlayer which can be obtained by a process comprising the step of feeding a substrate thermoplastic film through a conventional ink jet printer and ink-jet printing an image onto the surface of
20 the film, and then laminating the image-bearing film with at least a second sheet of a thermoplastic interlayer material. The composite printed interlayer preferably has a thickness of from about 30 to about 60 mils. The other thermoplastic sheets can be: blank; bear printed images or solid colors; transparent, semi-transparent, opaque or any solid, translucent
25 color such as red, green, blue, or white; otherwise visually distinct from the printing substrate.

EXAMPLES

The following examples are presented to illustrate the invention.
30 The examples are not intended to limit the scope of the invention in any manner. Together with the description of the invention and the teachings included herein, the Examples set forth the invention in such a manner

that one of ordinary skill in the art would have a clear concept of the invention claimed herein.

Test Methods

- Surface Roughness**, Rz, is determined from the 10 point average roughness as described in ISO-R468 and is expressed in microns. Surface roughness is measured using a Mahr Federal (Providence, RI) surfanalyzer. Surface Pattern Frequency is calculated from the surfanalyzer data by making a graph of the autocorrelation function vs. distance of the profilometer data. The autocorrelation data is analyzed by fast Fourier transform. The reported frequency of the surface pattern is the median frequency.

- Compressive Shear Adhesion Test**: Laminate adhesion (given in terms of compressive shear strength) is determined by the compressive shear test. The compressive shear strength is determined by sawing a laminate into six 2.54 cm x 2.54 cm chips. The chips are held in a jig at 45° and a compression testing instrument is used to place force on the chip at the rate of 0.25 cm/min. The amount of force to cause cohesive failure of the glass-PVB bond is the compressive shear strength of the laminate.

- Image Quality Test** Image quality was determined for each laminate by visually ranking the samples with respect to resolution and mottle.

- Accelerated Weathering Test** Laminates were prepared and the CIE L*, a*, b* color of the laminates was measured. The laminates were submitted for accelerated weathering according to the ASTM G90 cycle 2 protocol. The change in CIE L*, a*, b* color was measured as the samples returned from exposure. On average exposure to 480,000 langley corresponds to approximately 4 years of natural weathering.

Printing/Lamination Process

- The image of interest was ink jet printed onto the 30 mil thick interlayer using either commercially available or experimental inks. Prior to lamination the sheeting layers are conditioned to 27% RH for a minimum

- of 16 hours. For lamination, a layer of 15 mil clear interlayer is placed on the image bearing surface. A second 15 mil thick layer of interlayer was placed behind the image. The multi-layered structure is deaired either using a vacuum bag or nip roll process and autoclaved using standard lamination conditions. Once the laminate is autoclaved, the laminate is tested for adhesion using the compressive shear adhesion test. The results are given in Table 1 below. The laminate was also visually graded for image quality with respect to mottle and resolution. The results are given in Table 2 below.

10

Examples 1-4

The ink was ink jet printed onto PVB using an Epson 3000 printer. The samples were air dried and laminated as described above.

- 15 Example 1. The ink formulations are given below:

Color	Ink Formulations (weight percent)			
	Magenta	Yellow	Cyan	Black
Magenta Dispersion (7% pigment)	36.08			
Yellow Dispersion (7% pigment)		35.23		
Cyan Dispersion (5.5% pigment)			28.35	
Black Dispersion (7% pigment)				27.43
Dowanol® DPM	0.00	0.00	28.66	29.03
Dowanol® DPMA (dipropylene glycol methy	38.35	38.86	42.99	43.54
Dowanol® DPnP (dipropylene glycol mono-	25.57	25.91	0.00	0.00
Total	100.00	100.00	100.00	100.00

Example 2. The ink formulations are given below:

Color	Ink Formulations (weight percent)	
	Magenta	Black
Magenta Dispersion (20% pigment)	22.50	
Black Dispersion (15% pigment)		18.10
PUR 425/DPM	22.50	22.50
2-Pyrrolodione	15.00	17.00
Isopropanol	15.00	17.40
Dowanol® DPM	25.00	25.00
Total	100.00	100.00

Example 3. The ink formulation given below:

Color	Ink Formulations (weight percent)
	Yellow
Yellow Dispersion (20% pigment)	34.40
Dowanol® DPMA (dipropylene glycol methy	37.00
Dowanol® DPnP (dipropylene glycol mono-	24.60
PVP/DPM	4.00
Total	100.00

Example 4. The ink formulation is given below:

Color	Ink Formulations (weight percent)
	Magenta
Magenta Dispersion (20% pigment)	18.50
PVP/VA 635	1.50
Dowanol® DPM	80.00
Total	100.00

- 5 Comparative Example 1. The ink was obtained commercially from Mimaki and the samples were printed on a JV3 ink jet printer.

Comparative Example 2. The ink formulations are given below:

Color	Ink Formulations (weight percent)		
	Magenta	Yellow	Cyan
Magenta Dispersion (15% pigment)	28.5		
Yellow Dispersion (15% pigment)		28.5	
Cyan Dispersion (15% pigment)			22.5
DI Water	40.00	40.00	40.00
Dowanol® DPM	31.00	31.00	37.00
PYK 348	0.50	0.50	0.50
Total	100.00	100.00	100.00

- 10 Comparative Example 3. The ink formulation is given below.

Color	Ink Formulations (weight percent)
	Cyan
Cyan Dispersion (20% pigment)	27.25
Dowanol® DPM	72.75
Total	100.00

Table 1. Adhesion Results

Example	Color	%T	Adhesion, N/cm ²	Adhesion, psi
1	Cyan	82	1445	2096
	Magenta	84	1501	2178
	Yellow	94	1221	1772
	Black	72	1538	2232
2	Magenta	49	1473	2137
	Black	21	1288	1869
3	Yellow	91	1449	2102
4	Magenta	74	2026	2939
C1	Purple	52	592	859
	Green	78	618	896
	Black	47	846	1228
	Brown	49	600	871
C2	Cyan	72	570	827
	Magenta	71	875	1270
	Yellow	91	835	1211
C3	Cyan	63	970	1408

- Examples 5-7. The surface pattern on the sheeting used in Examples 5-7 and Comparative Examples 4 and 5 was generated by melt fracture. The surface pattern on the sheeting used in Comparative Example 7 was generated by embossing where the deairing channels are aligned in parallel rows as opposed to the more random deairing channels found on sheeting where the pattern was generated by melt fracture.

10 Table 2. Image Quality Results

Example	Image Quality			
	Pattern Generation	Roughness	Frequency	Acceptability
5	Melt Fracture	45	2.0	Yes
6	Melt Fracture	25	1.4	Yes
7	Melt Fracture	21	2.0	Yes
C4	Melt Fracture	31	0.70	No
C5	Melt Fracture	48	0.90	No
C6	Embossed	50	3.5	No

The lightfastness testing was performed as described above. The delta E values for examples 8-18 are less than or equal to 8 after 480,000 langley of exposure. The pigments given in Comparative Examples 7-9 were unexpectedly found to have poor lightfastness.

5

TABLE 3. Lightfastness Results

Example	Pigment	Delta E 480 KLangley
8	PY 120	2
9	PY 155	3
10	PY 128	3
11	PY 180	8
12	PY 95	6
13	PY 93	4
14	PV 19/PR 202	4
15	PR 122	2
16	PB 15:4	3
17	PB 15:3	2
18	PBI 7	0.7
C7	PY 14	67
C8	PY 110	19
C9	PY 139	>70

CLAIMS

WHAT IS CLAIMED IS:

1. A process for obtaining an image-bearing laminate having a laminate adhesive strength of at least about 1000 psi, the process comprising the steps: "ink jet" printing a digital image, using a pigmented ink, onto at least one surface of a thermoplastic polymer interlayer to obtain an image-bearing interlayer; and laminating the image-bearing interlayer between sheets of transparent materials to obtain an image-bearing laminate, wherein the thermoplastic interlayer is a polymer selected from: polyvinyl butyrals (PVB), polyurethanes, polyethylenes, polypropylenes, and polyesters, EVA and wherein the pigments comprise at least one pigment selected from the group consisting of PY 120; PY 155; PY 128; PY 180; PY 95; PY 93; PV19/PR 202; PR 122; PB 15:4; PB 15:3; and PBI 7.
2. The process of Claim 1 wherein the printing process additionally comprises the step of jetting the pigmented ink onto a roughened interlayer surface, the surface having a roughness (R_z) of from about 30 μm to about 60 μm and a Frequency of greater than 0.9 cycles/mm, wherein the ink comprises a dispersant and optionally comprises a binder in either an aqueous or non-aqueous vehicle.
3. The process of Claim 2 wherein the viscosity of the ink is in the range of from about 1 cps to about 30 cps measured at 25 °C.
4. The process of Claim 3 wherein the viscosity of the ink is in the range of from about 1 cps to about 20 cps.
5. The process of Claim 4 wherein the viscosity of the ink is in the range of from about 1 cps to about 15 cps.
6. The process of Claim 5 wherein the viscosity of the ink is in the range of from about 1 cps to about 12 cps.
7. The process of Claim 6 wherein the pigment is dispersed in a vehicle having a water content of no more than 16 wt%.

8. The process of Claim 7 wherein the vehicle comprises an organic solvent selected from the group consisting of: propylene glycol ethers; ethylene glycol butyl ethers; dipropylene glycol monomethyl ether acetate (DPMA); or mixtures of any of these.
- 5 9. The process of Claim 8 wherein the vehicle comprises DPMA.
10. The process of Claim 9 wherein the vehicle comprises DPMA and water.
11. The process of Claim 10 wherein the vehicle consists essentially of DPMA.
- 10 12. The process of Claim 8 wherein the ink comprises a dispersant but no binder.
13. The process of Claim 12 wherein the dispersant comprises a structured polymer.
14. The process of Claim 9 wherein the ink comprises a dispersant and
15 a binder.
15. The process of Claim 14 wherein the dispersant comprises: AB, BAB and ABC block copolymers, branched polymers and graft polymers.
16. The process of Claim 15 wherein the binder is selected from
20 binders in the group consisting of: polyurethane (PUR); polyvinyl pyrrolidone/polyvinyl acetate (PVP/VA); PVP; and mixtures of any of these.
17. The process of Claim 16 wherein the thermoplastic interlayer is polyvinyl butyral (PVB), polyethylene terephthalate (PET), PUR, or
25 ethylene vinyl acetate (EVA).
18. The process of Claim 17 wherein the interlayer is PVB.
19. The process of Claim 18 wherein the image is printed using a drop on demand (DOD) ink jet printing process.
20. The process of Claim 19 wherein the DOD process is a piezo
30 electric process.
21. The process of Claim 19 wherein the DOD process is a thermal ink jet printing process.

22. The process of Claim 18 wherein the image is printed using a continuous drop ink jet printing process.
23. A decorative laminate having an adhesive strength of at least about 1000 psi comprising at least one sheet of interlayer material bearing an image on at least one surface of the interlayer sheet, wherein the image was printed using an ink jet printing process comprising the step of jetting either an aqueous or solvent-based pigmented ink onto a roughened interlayer surface, the surface having a roughness (R_z) of from about 30 μm to about 60 μm and a Frequency of greater than 0.9, wherein the pigment comprises at least one pigment selected from the group consisting of PY 120; PY 155; PY 128; PY 180; PY 95; PY 93; PV19/PR 202; PR 122; PB 15:4; PB 15:3; and PBI 7; and wherein the ink has a viscosity that is sufficiently low that it can be jetted through an ink jet printing head without heating the printing head, and wherein the ink comprises a dispersant and optionally comprises a binder.
24. The laminate of Claim 23 wherein the interlayer is laminated between two sheets of glass.
25. The laminate of Claim 24 wherein the laminate has an adhesive strength of at least about 1400 psi.
26. The laminate of Claim 25 wherein the laminate has an adhesive strength of at least about 1700 psi.
27. The laminate of Claim 26 wherein the laminate has an adhesive strength at least about 1800 psi.
28. The laminate of Claim 27 comprising an image printed using at least two inks, wherein each ink, when printed onto the interlayer individually, has an adhesion of at least 1000 psi.
29. The laminate of Claim 28 wherein each ink, when printed onto the interlayer individually, has an adhesion of at least 1400 psi.
30. The laminate of Claim 29 wherein each ink, when printed onto the interlayer individually, has a Delta E after 480 KLangley of less than 10.

31. A thermoplastic interlayer sheet bearing an image on at least one surface of the interlayer sheet, the image being printed on the sheet by a process comprising the step: jetting either an aqueous or solvent-based pigmented ink onto a roughened interlayer surface, the surface having a roughness (R_z) of from about 30 μm to about 60 μm and a Frequency of greater than 0.9 cycles/mm, wherein the pigment comprises at least one pigment selected from the group consisting of PY 120; PY 155; PY 128; PY 180; PY 95; PY 93; PV19/PR 202; PR 122; PB 15:4; PB 15:3; and PBI 7; and wherein the ink has a viscosity that is sufficiently low that it can be jetted through an ink jet printing head without heating the printing head, and wherein the ink comprises a dispersant and optionally comprises a binder.
32. The interlayer of Claim 31 wherein the interlayer has a surface roughness Frequency of from about 1.0 cycles/mm to about 2.9 cycles/mm.
33. The interlayer of Claim 32 wherein the interlayer has a surface roughness Frequency of from about 1.1 cycles/mm to about 2.5 cycles/mm.
34. The interlayer of Claim 33 wherein the interlayer comprises PVB, PET, or PUR.
35. The interlayer of Claim 34 wherein the interlayer is PVB.

INTERNATIONAL SEARCH REPORT

PCT/US 03/26193

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 B32B17/10 B32B27/06 B32B31/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B32B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 6 077 374 A (HOPFE HAROLD HERBERT) 20 June 2000 (2000-06-20) column 1, lines 50-65; claim 1; example 1	1-35
A	WO 01/030919 A (CABOT CORP) 3 May 2001 (2001-05-03) page 5, lines 1-13 page 26, line 18 - page 27, line 22; tables 1-3,5-10,13,15,16	1-35
A	WO 02/18154 A (DIGIGLASS PTY LTD ; MC CLUSKEY GERARD MICHAEL (AU); REYNOLDS MILTON CH) 7 March 2002 (2002-03-07) cited in the application page 4, lines 10-15; claims 1,14,15,17,30	1-35

☐

Further documents are listed in the continuation of box C.

☒

Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *G* document member of the same patent family

Date of the actual completion of the international search

22 December 2003

Date of mailing of the international search report

05/01/2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Seiberlich, P

INTERNATIONAL SEARCH REPORT

Information on patent family members

PCT/US 03/26193

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 6077374	A	20-06-2000	AT 150363 T	15-04-1997
			BR 9407277 A	01-10-1996
			CA 2168115 A1	23-02-1995
			CN 1131927 A ,B	25-09-1996
			CZ 9600269 A3	15-05-1996
			DE 69402207 D1	24-04-1997
			DE 69402207 T2	28-08-1997
			EP 0714350 A1	05-06-1996
			ES 2101566 T3	01-07-1997
			JP 3448298 B2	22-09-2003
			JP 9501619 T	18-02-1997
			JP 2003238218 A	27-08-2003
			KR 174787 B1	20-03-1999
			WO 9505283 A1	23-02-1995
			US 5425977 A	20-06-1995
WO 0130919	A	03-05-2001	AU 1353401 A	08-05-2001
			AU 1353501 A	08-05-2001
			CN 1413236 T	23-04-2003
			EP 1226216 A1	31-07-2002
			EP 1228150 A1	07-08-2002
			JP 2003513137 T	08-04-2003
			JP 2003513138 T	08-04-2003
			WO 0130918 A1	03-05-2001
			WO 0130919 A1	03-05-2001
			US 6506245 B1	14-01-2003
WO 0218154	A	07-03-2002	US 6494943 B1	17-12-2002
			WO 0218154 A1	07-03-2002
			AU 8559001 A	13-03-2002
			CA 2420870 A1	07-03-2002
			EP 1322482 A1	02-07-2003